




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : C08G 18/08		A1	(11) International Publication Number: WO 98/41552
			(43) International Publication Date: 24 September 1998 (24.09.98)
(21) International Application Number: PCT/US98/05141		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 17 March 1998 (17.03.98)			
(30) Priority Data: 60/039,194 17 March 1997 (17.03.97) US			
(71) Applicant: THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Midland, MI 48674 (US).			
(72) Inventors: JAKUBOWSKI, James, J.; 3616 Jane Drive, Midland, MI 48642 (US). PATE, James, E., III; 933 West Walter Road, Sanford, MI 48657 (US). WILLKOMM, Wayne, R.; 306 Live Oak Lane, Lake Jackson, TX 77566 (US).			
(74) Agent: WILLIS, Reid, S.; Patent Dept., P.O. Box 1967, Midland, MI 48641-1967 (US).		<p>Published</p> <p><i>With international search report.</i></p> <p><i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	

(54) Title: CONTINUOUS PROCESS FOR PREPARING A POLYURETHANE LATEX



(57) Abstract

A polyurethane/urea/thiourea latex having a narrow molecular weight polydispersity and sub-micron particle size can be prepared by first preparing a high internal phase ratio (HIPR) emulsion of a polyurethane/urea/thiourea prepolymer, then contacting the emulsion with a chain-extending reagent under such conditions to form the polymer latex.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

CONTINUOUS PROCESS FOR PREPARING A POLYURETHANE LATEX

This invention relates to polyurethane/urea/thiourea latexes prepared from a high internal phase ratio emulsion of a urethane/urea/thiourea prepolymer.

Polyurethane/urea/thiourea latexes are generally prepared by chain extending the
5 reaction product of an organic diisocyanate and an organic compound having two active
hydrogen atoms such as polyalkylene ether glycols, poly(alkylene ether-alkylene thioether)
glycols, alkyd resins, polyesters and polyester amides. The diisocyanate is used in
stoichiometric excess so that the reaction product, also referred to as a
polyurethane/urea/thiourea prepolymer, is isocyanate terminated. The prepolymer is
10 typically prepared in the presence of a solvent. Examples of polyurethane prepolymer
preparations are described in U.S. Patents 3,178,310, 3,919,173, 4,442,259, 4,444,976, and
4,742,095, among others.

U.S. Patent 3,294,724 discloses the preparation of a film-forming urethane latex by
chain extending the isocyanate-terminated prepolymer with a piperazine compound. First,
15 the prepolymer is prepared by reacting a polyalkylene ether glycol with a diisocyanate. A
prepolymer emulsion is then formed, whereupon a piperazine compound dissolved in cold
water is added to the emulsion with stirring to form a stable chain-extended latex. A solvent
such as toluene or cyclohexanone is used either in the step to form the prepolymer or in the
chain extension step.

20 The solids content of a typical polyurethane latex tends to be in the range of 30 to 40
weight percent. For example, U.S. Patent 4,742,095 describes the preparation of a
polyurethane latex having a solids content of as high as 41 weight percent. To minimize
transport costs and drying times, it is desirable to prepare a polyurethane latex that
maximizes solids content without having to resort to additional concentration means such as
25 evaporation of water.

It would be advantageous to prepare a polyurethane/urea/thiourea latex in the
substantial absence of any ancillary organic solvents. It would be further advantageous to
prepare such a latex with controlled particle size and a narrow particle size distribution.
Finally, it would be desirable to prepare a polyurethane latex that has a solids content of at
30 least 45 percent by weight. Such a latex would be particularly useful as a carpet backing.

In one aspect, the present invention is a process for preparing a
polyurethane/urea/thiourea latex comprising the steps of: a) forming by a continuous
process a high internal phase ratio (HIPR) emulsion of a polyurethane/urea/thiourea

prepolymer in the presence of water and an emulsifying and stabilizing amount of a surfactant; and b) contacting the high internal phase ratio emulsion with a chain-extending reagent under such conditions to form the polyurethane/urea/thiourea latex; wherein the prepolymer is prepared by contacting a high molecular weight organic compound having at least two active hydrogen atoms with sufficient polyisocyanate, and under such conditions to ensure that the prepolymer is terminated with at least two isocyanate groups.

In another aspect, the present invention is a process for preparing a polyurethane/urea/thiourea latex comprising the steps of: a) continuously merging into a disperser and in the presence of an emulsifying and stabilizing amount of a surfactant, an aqueous stream having a flow rate R_1 and a polyurethane/urea/thiourea prepolymer stream having a flow rate R_2 ; b) mixing the merged streams with a sufficient amount of shear to form a high internal phase ratio emulsion; and c) mixing the high internal phase ratio emulsion with water and a chain-extending reagent to form a polyurethane/urea/thiourea latex; wherein $R_2:R_1$ is such that the polydispersity of the HIPR emulsion is not greater than 3 or the volume average particle size is not greater than 2 microns.

In another aspect, the present invention is a continuous process for preparing a polyurethane/urea/thiourea latex comprising the steps of: a) merging a stream containing a stoichiometric excess of a polyisocyanate with a stream containing a high molecular weight organic compound having at least two active hydrogen atoms into a static or an active mixer under such conditions to form a polyurethane prepolymer that is terminated with at least two end groups; b) forming an emulsion of the prepolymer by merging a stream containing the prepolymer with a stream containing water and in the presence of an emulsifying and stabilizing amount of a surfactant; and c) contacting a stream of the emulsion with a stream of a chain-extending reagent under such conditions to form a polyurethane/urea/thiourea latex.

In another aspect, the present invention is a polyurethane/urea/thiourea latex having a solids content of not less than 45 percent by weight, based on the total weight of the latex.

Figure 1 is a profile of the volume average particle size in microns (I) and polydispersity (II) of an HIPR emulsion, stabilized with linear sodium dodecylbenzene sulfonate, as a function of the urethane prepolymer to water flow rates (III) used to prepare the emulsion.

The polyurethane/urea/thiourea latex of the present invention can be prepared by reacting a polyurethane/urea/thiourea prepolymer with a chain-extending reagent in an aqueous medium and in the presence of a stabilizing amount of a surfactant. The polyurethane/urea/thiourea prepolymer can be prepared by any suitable method such as

those well known in the art. The prepolymer is advantageously prepared by contacting a high molecular weight organic compound having at least two active hydrogen atoms with sufficient polyisocyanate, and under such conditions to ensure that the prepolymer is terminated with at least two isocyanate groups.

5 The polyisocyanate is preferably an organic diisocyanate, and may be aromatic, aliphatic, or cycloaliphatic, or a combination thereof. Representative examples of diisocyanates suitable for the preparation of the prepolymer include those disclosed in U.S. Patent 3,294,724, column 1, lines 55 to 72, and column 2, lines 1 to 9, as well as U.S. Patent 3,410,817, column 2, lines 62 to 72, and column 3, lines 1 to 24. Preferred diisocyanates
10 include 4,4'-diisocyanatodiphenylmethane, 2,4'-diisocyanatodiphenylmethane, isophorone diisocyanate, *p*-phenylene diisocyanate, 2,6 toluene diisocyanate, polyphenyl polymethylene polyisocyanate, 1,3-bis(isocyanatomethyl)cyclohexane, 1,4-diisocyanatocyclohexane, hexamethylene diisocyanate, 1,5-naphthalene diisocyanate, 3,3'-dimethyl-4,4'-biphenyl diisocyanate, 4,4'-diisocyanatodicyclohexylmethane, 2,4'-diisocyanatodicyclohexylmethane,
15 and 2,4-toluene diisocyanate, or combinations thereof. More preferred diisocyanates are 4,4'-diisocyanatodicyclohexylmethane, 4,4'-diisocyanatodiphenylmethane, 2,4'-diisocyanatodi-cyclohexylmethane, and 2,4'-diisocyanatodiphenylmethane. Most preferred is 4,4'-diisocyanatodiphenylmethane and 2,4'-diisocyanatodiphenylmethane.


As used herein, the term "active hydrogen group" refers to a group that reacts with an
20 isocyanate group to form a urea group, a thiourea group, or a urethane group as illustrated by the general reaction:



where X is O, S, NH, or N, and R and R' are connecting groups which may be aliphatic, aromatic, or cycloaliphatic, or combinations thereof. The high molecular weight organic
25 compound with at least two active hydrogen atoms has a molecular weight of not less than 500 Daltons.

The high molecular weight organic compound having at least two active hydrogen atoms may be a polyol, a polyamine, a polythiol, or a compound containing combinations of amines, thiols, and ethers. Preferably, the high molecular weight organic compound having
30 at least two active hydrogen atoms is a diol, a diamine, a dithiol, an alcohol-amine, a thiol-amine, or an alcohol-thiol, and has a weight average molecular weight of not less than 500. Preferably, the high molecular weight organic compound having at least two active hydrogen

atoms is a polyalkylene glycol ether or thioether or polyester polyol or polythiol having the general formula:



where each R is independently an alkylene radical; R' is an alkylene or an arylene radical;
 5 each X is independently S or O, preferably O; n is a positive integer; and n' is a non-negative integer, with the proviso that n and n' are sufficiently large that the compound has a weight average molecular weight of not less than 500 Daltons, more preferably not less than 750 Daltons, and most preferably not less than 1000 Daltons. Preferably, the weight average molecular weight of the polyalkylene glycol is not greater than 20,000 Daltons, more preferably not greater than 10,000 Daltons, more preferably not greater than 5000 Daltons,
 10 and most preferably not greater than 3000 Daltons. The polyalkylene ether glycols and polyester polyols are preferred. Representative examples of polyalkylene ether glycols are polyethylene ether glycols, poly-1,2-propylene ether glycols, polytetramethylene ether glycols, poly-1,2-dimethylethylene ether glycols, poly-1,2-butylene ether glycol, and
 15 polydecamethylene ether glycols. Preferred polyester polyols include polybutylene adipate and polyethylene terephthalate.

A small amount of a low molecular compound with at least two active hydrogen atoms may be added along with to the high molecular weight organic compound having at least two active hydrogen atoms to increase the tensile strength of the resulting polymer.
 20 The molecular weight of the low molecular compound having at least two active hydrogen atoms is in the range of from 62 Daltons to 400 Daltons, and includes diols, dithiols, diamines, alcohol amines, alcohol thiols, and amine thiols. Diols including diethylene glycol, ethylene glycol, and dipropylene glycol are preferred. The amount of low molecular weight organic compound is preferably added in a sufficient amount to advantageously increase the
 25 tensile strength of the resulting polymer. More preferably, the amount of low molecular organic compound having at least two active hydrogen atoms is not less than 0.5 weight percent, most preferably not less than 1 weight percent based on the weight of the total compounds having active hydrogen atoms; and more preferably not greater than 10 weight percent, most preferably not greater than 5 weight percent based on the weight of the total
 30 compounds having active hydrogen atoms.

Preferably, the NCO:XH ratio, where X is O or S, preferably O, is not less than 1.1:1, more preferably not less than 1.2:1, and preferably not greater than 5:1.

The polyurethane prepolymer can be prepared by a batch or a continuous process by methods such as those well known in the art. For example, a stoichiometric excess of a diisocyanate and a polyol can be introduced in separate streams into a static or an active mixer, preferably in the presence of an activating amount of an organotin catalyst such as stannous octoate, and at a temperature suitable for controlled reaction of the reagents, typically from 40°C to 100°C. The reaction is carried to substantial completion in a plug flow reactor to form the prepolymer. Upon substantial completion of the reaction, the temperature of the prepolymer may be adjusted for the formation of the HIPR emulsion.

The HIPR emulsion can be prepared by any suitable method such as those well known in the art. (See, for example, U.S. Patent 5,539,021, column 1, lines 9 to 45.) In the process of the present invention, the temperature at which the HIPR emulsion is prepared is not critical; however, it may be desirable in some instances to prepare the emulsion at subambient temperatures, because water slowly reacts with diisocyanate groups to form amines and CO₂, and it may be advantageous to suppress premature reaction of water and the prepolymer. Furthermore, the preferred temperature for preparing the HIPR emulsion is dependent on the residence time, that is, the time between the formation of the HIPR emulsion and the contact of the emulsion with the chain-extending reagent. In general, the shorter the residence time, the greater the flexibility in selection of temperature is.

In a preferred method of preparing the HIPR emulsion, a flowing stream containing the prepolymer is merged with a flowing stream containing water with sufficient shear to form the HIPR emulsion. An emulsifying and stabilizing amount of a surfactant is also present, either in the stream containing the prepolymer, in the stream containing the water, or in a separate stream. The relative rates of the stream containing the prepolymer (R_p) and the stream containing the water (R_w) are preferably such that the polydispersity of the HIPR emulsion (the ratio of the volume average diameter and the number average diameter of the particles or droplets, or D_v/D_n) is not greater than 5, more preferably not greater than 3, more preferably not greater than 2, more preferably not greater than 1.5, and most preferably not greater than 1.3; or the volume average particle size is not greater than 2 microns, more preferably not greater than 1 micron, more preferably not greater than 0.5 micron, and most preferably not greater than 0.3 micron. Furthermore, it is preferred that the HIPR emulsion be prepared in a continuous process without phase inversion or stepwise distribution of an internal phase into an external phase.

The surfactant is sometimes used as a concentrate in water. In this case, a stream containing the surfactant is advantageously first merged with a stream containing the prepolymer to form a prepolymer/surfactant mixture. Although an HIPR emulsion can be prepared in this single step, it is preferred that a stream containing the prepolymer and the surfactant be merged with a water stream to dilute the surfactant and to create an HIPR emulsion.

Referring to Figure 1, the profile of the polydispersity and volume average particle size of the HIPR emulsion prepolymer prepared with 1 percent RHODACAL™ LDS-22 surfactant (sodium dodecylbenzene sulfonate, a trademark of Rhone Poûlenc) is illustrated.

10 The region where the oil:water feed rate ratio ($R_2:R_1$) is in the range of 5:1 to 9.2:1 represents the preferred operating range of $R_2:R_1$ for the given prepolymer (prepared by reacting 30 weight percent of a 50:50 mixture of 4,4'-diisocyanatodiphenylmethane and 2,4'-diisocyanatodiphenylmethane with 70 weight percent of a polypropylene oxide diol having a weight average molecular weight of 2000), and the type and amount of surfactant used.

15 When the HIPR emulsion is prepared using 3 percent by weight DeSULF™ TLS-40 surfactant (active ingredient is triethanolamine lauryl sulfate, a trademark of DeForest Enterprise, Inc.), the preferred $R_2:R_1$ is from 5:1 to 8:1. When the surfactant is 3 percent by weight DeSULF™ DBS-60T surfactant (active ingredient is triethanolamine dodecylbenzene sulfonate, a trademark of DeForest Enterprise, Inc.) the preferred $R_2:R_1$ is from 3.5:1 to 6:1.

20 An external surfactant, which may be cationic, anionic, or nonionic, is preferably used to prepare the HIPR emulsion. Suitable classes of surfactants include, but are not restricted to, sulfates of ethoxylated phenols such as poly(oxy-1,2-ethanediyl) α -sulfo- ω (nonylphenoxy) ammonium salt; alkali metal fatty acid salts such as alkali metal oleates and stearates; polyoxyalkylene nonionics such as polyethylene oxide, polypropylene oxide, 25 polybutylene oxide, and copolymers thereof; alcohol alkoxylates; ethoxylated fatty acid esters and alkylphenol ethoxylates; alkali metal lauryl sulfates; amine lauryl sulfates such as triethanolamine lauryl sulfate; quaternary ammonium surfactants; alkali metal alkylbenzene sulfonates such as branched and linear sodium dodecylbenzene sulfonates; amine alkyl benzene sulfonates such as triethanolamine dodecylbenzene sulfonate; anionic and nonionic 30 fluorocarbon surfactants such as fluorinated alkyl esters and alkali metal perfluoroalkyl sulfonates; organosilicon surfactants such as modified polydimethylsiloxanes; and alkali metal soaps of modified resins. If the prepolymer is self-emulsifying by inclusion of emulsifying nonionic, cationic, or anionic groups, then an external surfactant may or may not be necessary.

Generally, higher surfactant concentrations result in smaller diameter particles, but surfactant concentrations that are too high tend to deleteriously affect the properties of products such as films prepared from the HIPR emulsion. A person of ordinary skill in the art can readily determine the appropriate surfactant concentration for the particular end use.

5 Although it is possible to first dissolve the prepolymer in a solvent for the prepolymer prior to forming the HIPR emulsion, it is preferred to prepare the HIPR emulsion in the substantial absence of a solvent, more preferably in the absence of a solvent. As used herein, the term "in the substantial absence of a solvent" means that a solvent for the prepolymer represents not more than 10 weight percent, preferably not more than 5 weight
10 percent, more preferably not more than 1 weight percent, and most preferably not more than 0.1 weight percent of the HIPR emulsion based on the weight of the prepolymer and the solvent.

The inclusion of a solvent often adds an unnecessary expense to the manufacture of the end-use product. Moreover, solvent removal, when necessary to obtain acceptable
15 physical properties of the product, is also an expensive as well as a time-consuming step. Thus, a preferred process of the present invention represents an advance in the art of the preparation of urethane latexes.

A polyurethane/urea/thiourea polymer is prepared by contacting the HIPR emulsion of the prepolymer with a chain-extending reagent, which is a compound that contains
20 functional groups that react with isocyanate groups to form urethane, urea, or thiourea groups. Chain-extending reagents are well known in the art.

The HIPR emulsion is preferably first diluted with sufficient water to form a prepolymer latex having a disperse phase to aqueous phase ratio that is less than 3:1. Although water can be used as a chain-extending agent, other chain-extending agents are
25 preferred for building of molecular weight. Therefore, it is preferred that the prepolymer latex be contacted with the preferred chain-extending reagent before substantial reaction takes place between water and the prepolymer. Preferred chain-extending reagents include aliphatic, cycloaliphatic, aromatic polyamines, and alcohol amines. More preferred chain-extending reagents are alcohol monoamines such as monoethanol amine and diethanol
30 amine, and diamines including hydrazine, ethylene diamine, propylene-1,2-diamine, propylene-1,3-diamine, tetramethylenediamine, hexamethylenediamine, 4,4'-dimethylamino-3,3'-dimethyl-diphenylmethane, 4,4'-diamino-diphenylmethane, 2,4-diaminotoluene, 2,6-diaminotoluene, aminoethylethanolamine, and piperazine. Water-soluble diamines are most preferred. Piperazine is an example of a most-preferred chain-extending agent.

The chain-extending reagent is preferably the limiting reagent because it is desirable to avoid residual chain-extending reagent, particularly diamine, in the final latex. Thus, in a preferred method of preparing the polyurethane/urea/thiourea latex, an aqueous solution of a diamine is contacted with a stoichiometric excess of a latex of the prepolymer (that is, a
5 stoichiometric excess of isocyanate groups). After the diamine is substantially completely reacted, the resultant latex is preferably allowed to stand for a sufficiently long time so that the remaining isocyanate groups react with the water. The preferred latex is a polyurethane/urea latex having a volume average particle size of not greater than 1 micron, more preferably not greater than 0.5 micron, and most preferably not greater than
10 0.4 micron, with a polydispersity that is preferably not greater than 2, more preferably not greater than 1.5, and most preferably not greater than 1.3.

It has been surprisingly discovered that the volume average particle size and polydispersity of a final polyurethane/urea/thiourea latex prepared from an HIPR emulsion of a polyurethane/urea/thiourea prepolymer by the process of the present invention is generally
15 less than the particle size and polydispersity of a polyurethane/urea/thiourea latex not prepared from an HIPR emulsion of a polyurethane/urea/thiourea prepolymer, for a given surfactant, and at a given concentration of the surfactant.

It is further surprising that a polyurethane latex with high solids content that is at least 45 percent by weight, preferably at least 50 percent by weight, more preferably at least
20 55 percent by weight, based on the weight of the latex, can be prepared by the process of the present invention. This high solids latex can be prepared without resorting to costly removal of water from a more dilute latex.

The polyurethane/urea/thiourea latexes of the present invention are useful for applications for latexes with controlled particle size and narrow size distributions are
25 especially important. Such applications include films, floor coatings, and adhesives, especially for carpet-backing applications.

The following examples are for illustrative purposes only and are not intended to limit the scope of this invention. All percentages are in weight percent unless otherwise stated.

Example 1

30 A urethane/urea prepolymer was prepared by reacting 70 percent by weight of a poly(propylene oxide) polyol VORANOL™ 2120 polyol (a trademark of The Dow Chemical Company) with 30 percent by weight of ISONATE™ 50 MDI (a trademark of The Dow Chemical Company; a 50:50 mixture of 4,4'-diisocyanatodiphenylmethane and 2,4'-diisocyanatodiphenylmethane). The following processes were carried out at 10°C. The

prepolymer was fed continuously at a rate of 31.4 g/minute through a 1/2-inch (1.25 cm) stainless-steel tube fitted to one arm of a T. A 20-percent aqueous solution of a sodium dodecylbenzene sulfonate (RHODACAL™ DS-10, a trademark of Rhone Poûlenc) was fed continuously at a rate of 4.7 g/minute through a 1/8-inch (0.31 cm) stainless-steel tubing fitted to the other arm of the T. The two streams were combined and passed through a static mixer to form a non-emulsified blend. The blend was then fed into a 1/2-inch (1.25 cm) stainless-steel tube fitted to one arm of a T attached to the input of a 70-mL centrifugal pump. Concurrently, water was pumped through a 1/8-inch (0.31 cm) tetrafluoroethylene tubing fitted to the other arm of the T, at the rate of 3.0 g/minute. The two streams were merged and mixed together under shear in the centrifugal pump operating at 650 rpm to form an HIPR emulsion.

The HIPR emulsion was diluted in a second centrifugal pump by feeding the emulsion into a 1/2-inch (1.25 cm) stainless-steel tube fitted to one arm of a T attached to a centrifugal pump. Concurrently, water was pumped at a rate of 10 g/minute through 1/4-inch (0.63 cm) tetrafluoroethylene tubing fitted to the other arm of the T. The two streams were mixed with the centrifugal pump operating at 900 rpm.

Chain extension was accomplished in a third centrifugal pump by feeding the diluted emulsion into a 1/2-inch (1.25 cm) stainless-steel tube fitted to an arm of a T that was attached to the input of a centrifugal pump. Concurrently, a 4.2 percent aqueous solution of piperazine was pumped at a constant rate of 22.0 g/minute through a 1/4-inch (0.63 cm) tetrafluoroethylene tube fitted to the other arm of the T. The two streams were mixed in the centrifugal pump operating at 650 rpm. The product was collected and allowed to stand overnight to allow water to react with the remaining isocyanate groups. The resulting stable poly(urethane/urea) latex was found to have a solids content of 47.1 percent by weight, a volume average particle size of 0.342 micron, and a polydispersity of 1.2, as measured by a Coulter LS 230 particle size analyzer.

Example 2

The prepolymer was prepared by combining VORANOL™ 5287 polyol (63.35 percent by weight, a trademark of The Dow Chemical Company), ISONATE™ 50 MDI (33.3 percent by weight), diethylene glycol (1.35 percent by weight), and polyethylene oxide monol having a molecular weight of 950. The following processes were conducted at ambient temperature (19°C).

The prepolymer was fed continuously at rate of 32.1 g/minute through a first arm fitted to a first T. DeSULF™ DBS-60T surfactant (a 60 percent aqueous solution of

triethanolamine dodecylbenzene sulfonate, a trademark of DeForest Enterprises, Inc.) was fed at a rate of 1.61 g/minute through a first arm of a second T, and merged with a water stream flowing at a rate of 5.5 g/minute through the second arm of the second T. The prepolymer stream and the water/surfactant stream were merged at the first T and passed
5 through a static mixer and then fed to the input port of a IKA-SD 41 SUPER-DISPAX™ dispersing instrument (a trademark of IKA-WORKS, Inc.), which was a rotor/stator device that was operated at 1200 rpm.

The ratios of feeds into the dispersing instrument were 81.9 percent prepolymer, 4.1 percent surfactant solution, and 14.0 percent water. The HIPR emulsion formed in the
10 dispersing instrument had a volume average particle size of 0.265 micron and a polydispersity of 3.1, as measured by a Coulter LS130 particle size analyzer.

Chain extension was accomplished in a LIGHTNIN™ model .025 LB in-line blender (a trademark of GREEY/LIGHTNIN). The HIPR emulsion from the dispersing instrument was fed into a first arm attached to a third T and merged with an aqueous stream fed
15 through a second arm of the third T at the rate of 5.1 g/minute. The output of the combined streams was fed into one arm of a fourth T, which was attached to the input of the in-line blender. Concurrently, a 10 percent aqueous piperazine solution was pumped at a constant rate of 18.0 g/minute (0.75 equivalents, based on the isocyanate groups of the prepolymer) through the other arm of the fourth T. The two streams were mixed in the in-line blender
20 operating at 1500 rpm. The product was collected and allowed to stand overnight to allow water to react with the remaining isocyanate groups. The resulting stable poly(urethane/urea) latex was found to have a solids content of 56.0 percent by weight, a volume average particle size of 0.256 micron, and a polydispersity of 3.5, as measured by a Coulter LS 230 particle size analyzer.

25 Example 3

The same general procedure used to prepare the latex from Example 2 was repeated. In this example, the surfactant was DeSULF™ LTS-40 surfactant (a 40 percent aqueous solution of triethanolamine lauryl sulfate, a trademark of Deforest Enterprises, Inc.) and the flow rates were prepolymer, 32.0 g/minute; surfactant, 2.4 g/minute; and water,
30 3.5 g/minute. The ratios of the components that were fed into the disperser were prepolymer, 84.4 percent; surfactant solution, 6.3 percent; and water, 9.2 percent. The HIPR emulsion had a volume average particle size of 0.182 micron and a polydispersity of 1.6, as measured by a Coulter LS130 particle size analyzer.

The aqueous stream used to dilute the HIPR emulsion was flowed at a rate of 4.6 g/minute, and the piperazine solution was pumped at a rate of 17.9 g/minute. The final poly(urethane/urea) latex was found to have a solids content of 57.0 percent by weight, a volume average particle size of 0.188 micron, and a polydispersity of 1.9.

CLAIMS:

1. A process for preparing a polyurethane/urea/thiourea latex comprising the steps of:

- 5 a) forming by a continuous process a high internal phase ratio emulsion of a polyurethane/urea/thiourea prepolymer in the presence of water and an emulsifying and stabilizing amount of a surfactant; and
- b) contacting the high internal phase ratio emulsion with a chain-extending reagent under such conditions to form a polyurethane/urea/thiourea latex;

10 wherein the prepolymer is prepared by contacting a high molecular weight organic compound having at least two active hydrogen atoms with sufficient polyisocyanate, and under such conditions to ensure that the prepolymer is terminated with at least two isocyanate groups.

2. The process of Claim 1 wherein the polyurethane/urea/thiourea prepolymer is a polyurethane prepolymer.

15 3. The process of either of Claims 1 or 2 wherein the polyurethane prepolymer is prepared by contacting a stoichiometric excess of a polyisocyanate with a polyalkylene glycol ether or a polyester polyol, wherein the polyalkylene glycol is a polyethylene ether glycol, a poly-1,2-propylene ether glycol, a polytetramethylene ether glycol, a poly-1,2-dimethylethylene ether glycol, a poly-1,2-butylene ether glycol, or a polydecamethylene ether glycol, or a combination thereof, and wherein the polyester polyol is a polyethylene terephthalate or a polybutylene adipate and wherein the polyisocyanate is 4,4'-diisocyanatodiphenylmethane, 2,4'-diisocyanatodiphenylmethane, *p*-phenylene diisocyanate, 2,6 toluene diisocyanate, polyphenyl polymethylene polyisocyanate, 1,3-bis(isocyanatomethyl)cyclohexane, 1,4-diisocyanatocyclohexane, hexamethylene diisocyanate, 1,5-naphthalene diisocyanate, 3,3'-dimethyl-4,4'-biphenyl diisocyanate, 4,4'-diisocyanatodicyclohexylmethane, 2,4'-diisocyanatodicyclohexylmethane, isophorone diisocyanate, or 2,4-toluene diisocyanate, or combinations thereof.

25

4. The process of any of Claims 1 to 3 wherein the surfactant is a sulfate of an ethoxylated phenol, an alkali metal alkylbenzene sulfonate, an amine alkylbenzene sulfonate, an alkali metal lauryl sulfate, an amine lauryl sulfate, a polyoxyalkylene, an alkylphenol ethoxylate, or a quaternary ammonium surfactant, or a combination thereof.

30

5. The process of any of Claims 1 to 4 wherein the chain-extending reagent contains water.

6. The process of any of Claims 1 to 5 wherein the chain-extending reagent contains monoethanol amine, diethanol amine, hydrazine, aminoethylethanolamine, ethylene diamine, propylene-1,2-diamine, propylene-1,3-diamine, tetramethylenediamine, hexamethylenediamine, 4,4'-dimethylamino-3,3'-dimethyldiphenylmethane, 4,4'-diamino-
5 diphenylmethane, 2,4-diaminotoluene, 2,6-diaminotoluene, or piperazine, or a combination thereof.

7. The process of Claim 6 wherein the chain-extending reagent is an aqueous solution of piperazine, and the high internal phase ratio emulsion is formed in the substantial absence of a solvent.

10 8. The process of any of Claims 1 to 7 wherein the high internal phase ratio emulsion is prepared by the steps of:

a) continuously merging into a disperser and in the presence of an emulsifying and stabilizing amount of a surfactant, an aqueous stream having a flow rate R_1 and a polyurethane/urea/thiourea prepolymer stream having a
15 flow rate R_2 ; and


b) mixing the merged streams with a sufficient amount of shear to form a high internal phase ratio emulsion without phase inversion or stepwise distribution of an internal phase into an external phase;

wherein $R_2:R_1$ is such that the polydispersity of the high internal phase ratio emulsion is not
20 greater than 3 or the volume average particle size is not greater than 2 microns.

9. The process of any of Claims 1 to 8 wherein the polyurethane/urea/thiourea prepolymer is prepared by a continuous process of merging a stream containing 4,4'-diisocyanatodiphenylmethane or 2,4'-diisocyanatodiphenylmethane, or a combination thereof with a stream containing a polyethylene glycol ether having a weight average molecular
25 weight of not greater than 3000 Daltons and not less than 750 Daltons, wherein the surfactant is sodium dodecylbenzene sulfonate.

10. A polyurethane/urea/thiourea latex having a solids content of not less than 45 percent by weight, based on the total weight of the latex.

FIG. 1



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 98/05141

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C08G 18/08
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4742095 A (PETER H. MARKUSCH ET AL), 3 May 1988 (03.05.88)	1-10
A	US 5124073 A (FRIEDRICH GOFFING ET AL), 23 June 1992 (23.06.92)	1-10
A	NO 9639461 A1 (THE DOW CHEMICAL COMPANY), 12 December 1996 (12.12.96)	1-10

☐ Further documents are listed in the continuation of Box C. ☒ See patent family annex.

- * Special categories of cited documents:
- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

23 June 1998

Name and mailing address of the ISA/
European Patent Office, P.B. 5818 Patentlaan 2
NL-2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Date of mailing of the international search report

16. 07. 1998

Authorized officer

JACK HEDLUND

INTERNATIONAL SEARCH REPORT
Information on patent family members

09/06/98

International application No.

PCT/US 98/05141

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4742095 A	03/05/88	CA 1304869 A US 4879322 A	07/07/92 07/11/89
US 5124073 A	23/06/92	DE 3905007 A DE 59004064 D EP 0384165 A,B ES 2047167 T JP 2261824 A	23/08/90 00/00/00 29/08/90 16/02/94 24/10/90
WO 9639461 A1	12/12/96	AU 5726396 A EP 0830414 A NO 975642 A US 5539021 A US 5688842 A	24/12/96 25/03/98 04/12/97 23/07/96 18/11/97